

**NONAQUEOUS DISPERSION OF SUPERFINE ZINC OXIDE PARTICLES AND ITS PREPARATION**

Veröffentlichungsnummer JP11278838

Veröffentlichungsdatum: 1999-10-12

Erfinder: KONO HIROYUKI

Anmelder: KASEI CO C I

Klassifikation:

- Internationale: **C01G9/02; B01J13/00; B01J19/08; C09D7/12; C09D7/12; C01G9/00; B01J13/00; B01J19/08; C09D7/12; C09D7/12; (IPC1-7): C09D7/12; C01G9/02; B01J13/00; B01J19/08**

- Europäische:

Anmeldenummer: JP19980095160 19980325

Prioritätsnummer(n): JP19980095160 19980325

**Datenfehler hier melden**

**Zusammenfassung von JP11278838**

PROBLEM TO BE SOLVED: To provide a nonaq. dispersion of superfine zinc oxide particles which do not aggregate in the nonaq. dispersion and can easily be redispersed, and its preparation process.  
SOLUTION: Zinc is heated and vaporized by a DC arc plasma process and the resultant zinc vapor is oxidized and cooled to form rod-shaped superfine particles of hexagonal zinc oxide giving pH 6.5-7.5 to a 20 wt.% aq. dispersion of the particles and having 5-70 nm average particle diameter. The particles, together with a dispersant, are dispersed in an org. solvent to obtain the objective nonaq. dispersion of superfine zinc oxide particles.

Daten sind von der **esp@cenet** Datenbank verfügbar - Worldwide